

RAMAPET N1

Sales Specification

Polyethylene Terephthalate (PET) Resin

Manufacturing site test method reference

“Ottana Polimeri Srl”, Ottana

Property	Unit	Test method	RAMAPET N1 values
Intrinsic Viscosity	dl/g	1/MA/002	0.80 ± 0.02
Acetaldehyde	ppm	1/MA/004	Max 1
Colour L*	-	1/MA/003	Min 84
Colour a*	-	1/MA/003	-2.5 to -0.5
Colour b*	-	1/MA/003	-4 to 1.5
Pellet weight	Pieces/gram	1/MA/015	60 ± 5
Fines	Wt%	1/MA/001	Max 0.05

Ottana (NU)-Sardinia- Italy

July 2010

Daniela Montesu
Quality Assurance /Quality Control Manager

Neither UAB Ottana Polimeri Europe and it's Italian Branch, Ottana Polimeri Srl nor its marketing affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness of your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product, and nothing herein waives any of the Seller's conditions of sale.

UAB Ottana Polimeri Europe (Italian branch) and Ottana Polimeri Srl

Strada Provinciale 17 Km 18;

08020 Ottana (UN)

Registration Number: 07012450966

www.indoramapolymers.com

Tel: +390 784728222; Fax: +390784728246