



versalis

[Mbx.info.styrenics@versalis.eni.com](mailto:Mbx.info.styrenics@versalis.eni.com)

## PROVISIONAL DATA SHEET

Extir®  
Expandable polystyrene

VERDI PD VM A3000 AE

### Product description

Extir Verdi PD VM A3000 AE is an HBCD-free flame retardant expandable polystyrene in the form of spherical beads of medium particle size, containing pentane as blowing agent. Extir does not contain CFC or HCFC.

Extir Verdi PD VM A3000 AE is an improvement of A 3000 AE showing an improved thermal conductivity as VR A3000 AE.

Extir Verdi PD VM A3000 AE is used for production of shaped mouldings with section greater than 8 mm and of medium-high density blocks.

### Technical data

Bulk density	kg/m <sup>3</sup>	<b>590 - 630</b>
Particle size	mm	<b>0.6 - 1.0</b>
Minimum apparent density		
• on a continuous pre-expander after one expansion	kg/m <sup>3</sup>	<b>17</b>
• on a continuous pre-expander after two expansions	kg/m <sup>3</sup>	<b>not appl</b>
• on a discontinuous pre-expander	kg/m <sup>3</sup>	<b>17</b>
Density range normally used	kg/m <sup>3</sup>	<b>16 - 30</b>

### Applications

Extir Verdi PD VM A3000 AE has an improved thermal conductivity value, specially at low density. Extir Verdi PD VM A3000 AE is used mainly in building and industrial packaging applications where, for legislative or safety reasons, the use of a flame retardant material is required.

Typical applications are:

- industrial packaging (e.g. cathode ray tube protection)
- medium / high density blocks for thermal insulation
- window dressing, theatre backgrounds
- moulded panels for underfloor heating
- moulded or block-cut building components

## Processing

Extir Verdi PD VM A3000 AE can be easily pre-expanded over a wide density range from 15 to 30 kg/m<sup>3</sup>.

The recommended ageing time before moulding obviously depends on the pre-expanded density and ranges from 6 to 72 hours.

Extir Verdi PD VM A3000 AE can be moulded both on shape or block moulding machines.

## General information

It is recommended that the product be kept in a dry well ventilated store between 15-20°C.

For product packaged in octabins the guaranteed shelf-life is one month; product in steel drums has a six month guaranteed shelf-life.

During processing of Expandable Polystyrene any sparks or naked flames must be avoided and smoking should be forbidden. Adequate electrical grounding of machinery and of pneumatic conveyance lines is recommended.

For further information concerning storage, packaging and processing precautions please refer to "Styrenics - Technical data sheets" and the "Extir Safety Data Sheet".

Regarding "flame retardant" properties, articles made from Extir Verdi VM AE are undergoing certification process for B1 nach DIN 4102. The results of the test done in our laboratories comply with the standards.

The action of the flame retardant additive is exerted only after the elimination of blowing agent and, therefore, only after Extir AE has been transformed into foamed articles (suitably aged where necessary).

Issue 02/15

All indicated data refer to natural grades.

The data, information and suggestions are provided for guidance purposes only.

The Company accepts no responsibility for the results obtained therefrom, as neither for their utilization in infringement of possible patent rights.

On the subject of the experimental product the Company reserves the right to change without prewarning the characteristics to optimize the performance and the cost.

This Sheet is valid for six month from the revision date.