

FT – 06 : F 301 - PP

PRODUCT DESCRIPTION: Polypropylene homopolymer with basic stabilization; propylene is the only monomer used for producing the above-mentioned grade; there are not used plasticizers or colored master batches. The product has natural color.

APPLICATIONS: extrusion, raffia tapes.

PROPERTIES	UM	VALUES	TEST METHOD
PHYSICAL			
Melt Flow Index (230 °C / 2.16 kg)	g/10min	1,5	ISO 1133 B
Density (23 °C)	g/cm ³	0,9	ISO 1183
MECHANICAL			
Yield Strength (23 °C, v=50mm/min)	MPa	25	ISO 527/1,2
Yield stress (23 °C, v=50mm/min)	%	9	ISO 527/1,2
Flexural Modulus (23 °C, v=2mm/min, secant)	MPa	1000	ISO 178
IZOD Impact Strength (23 °C, slotted specimen)	KJ/m ²	3	ISO 180/1A
THERMAL			
VICAT Softening Temperature (A - 50°C/h-10N)	°C	150	ISO 306/A
Heat deflection temperature (A-120 °C/ h-1.80 Mpa)	°C	50	ISO 75 B

Note:

- The medium value of the mechanical and thermal properties is measured on the standard samples made by injection process (ISO 3167/ ISO 1873-2) conditioned at room temperature (ISO 291)

ADDITIONAL INFORMATIONS:

- The monomers and additives used to produce this product are accepted to be used in accordance with the requirements of Regulation 10/2011/EC and later modifications and completions (Regulation no. 202/2014 and Regulation no. 174/2015), relating to plastic materials and articles intended to come into contact with food.
- Processing information:**
 - Recommended melt temperature: 200-230°C;
 - Thermal profile recommended for extrusion: 200-280°C depending on the type of equipment.
- Packing/delivery:**
 - Packing: 25 kg bags or 1000 kg big-bags
 - Delivery: CP4 Euro pallets (1375 kg /pallet), big-bags (1000 kg) and bulk in container-liner.

OTHER INFORMATIONS:

- The **MSDS** is available by Sales Marketing Rompetrol Refining offices for the customers. The MSDS contains necessary information in order to ensure customers' own safe in handling and processing activity.
- CONTACT INFORMATION:**
 S.C.ROMPETROL REFINING SA
 ADDRESS: B-dul Navodari nr 215, Pavilion Administrativ, Navodari, Judetul Constanta, ROMANIA
 TEL:+ (40) 241 507 090 | FAX + (40) 241 506918
 office.rafinare@rompetrol.com
www.rompetrol-rafinare.ro
www.rompetrol.com